
RMA 66**Typical Properties**

| | |
|---|--|
| Inherent Viscosity | 0.95 (ASTM D1243-79) |
| Relative Viscosity | 2.25 ± .03 (1.0% Cyclohexanone @25°C) |
| K-Value | 66.0 ±1 (0.5gm/100m Cyclohexanone@25°C) |
| Bulk Density (g/cc) | .50 (ASTM D 1895-89) |
| Volatiles (%) | 0.8 (ASTM D3030-84) |
| Particle Size (ASTMD1921-89) | |
| Through 40 mesh | 100 |
| Through 200 mesh | 10 |
| Cell Classification (ASTM D1755) | GPA-15050 |
| CAS Number | 9002-86-2 |

TECHNICAL DATA SHEET

Disclaimer

This information is considered accurate and reliable as of the date appearing above and is presented in good faith. Because use conditions and applicable laws may differ from one location to another and may change with time, Recipient is responsible for determining whether the information in this document is appropriate for recipient's use. Since RMA has no control over how this information may be ultimately used, all liability is expressly disclaimed and RMA assumes no obligation or liability therefore. No warranty, express or implied, is given nor is freedom from any patent owned by RMA or others to be inferred.