

* F Versions typically indicate Flooring grade cuts of the same resin which inherently do not qualify for film grade or solution grade applications because they do not exceed seed/spec counts and early color requirements. They perform equally with their non F counterparts as they are certified equally as itemized below:

K Value (0.5gm/100ml Cyclohexanone @ 25 ° C)	53
Appearance (Visual Observation)	Free Flowing White Powder
Inherent Viscosity (ASTM D 1243-79)	.59 +/- .02
Relative Viscosity (1.0% in Cyclohexanone @ 25 ° C)	1.68 +/- .03
Apparent Bulk Density (g/cc) (ASTM D 1895-69)	.75 +/- .05
Bound Vinyl Acetate (%)	13 +/- 1.0
Particle Size Distribution (ASTM D 1921-63)	
Thru 40 mesh (% minimum)	100
Thru 200 mesh (% maximum)	30
Volatiles (% Max) (ASTM D 3030-79)	0.1
CAS Number	94766-13-9

All statements, information and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that any measures may not be required.